

Magical Red E5B

Quinacridone

C.I. Pigment Red 19
Colour Index No. 73900



Technical Application Data

	HDPE	PVC
Heat Stability(C°)	300	—
Light Fastness SD $\frac{1}{3}$ Full Shade	8	8
Light Fastness SD $\frac{1}{3}$ Reduction	8	8
Weather Fastness SD $\frac{1}{3}$ Full Shade	4-5	4-5
Weather Fastness SD $\frac{1}{3}$ Reduction	4	4-5
Fastness to bleed	—	5

Physical Characteristics

CAS No:	1047-16-1
Density(g/cm ³)	1.45
Alkali resistance	5
Acid resistance	5
Specific surface(m ² /g)	98

Range of Applications

						Spin Dyeing	
LDPE	●	PP	●	PC	●	PP	●
HDPE	●	Rubber	●	PBT	●	PET	●
PUR	●	PS/SAN	●	PA	●	PA	●
PVC	●	ABS	●	POM	●	PAN	●

Commentary

Quinacridone pigment with excellent fastness properties. Recommended for high-tech solutions. Applications in most plastics. Not suitable as shading pigment in polar engineering polymers such as POM or ABS.

Note : Data Presented above is based on our present knowledge and is with intentions of providing general guidelines for use of our products. These products are offered by TINTEC without any kind of guarantee. We recommend that customers should test the suitability of these products in their end application before use.